



TEST REPORT

No. : SHMR110201114

Date : Mar.3,2011

Page: 1 of 3

The following sample(s) was/ were submitted and identified on behalf of the client as:

Sample Name : WPC
Sample No. : SHMR110201114
SGS Ref. No. : 10547219
Product specification : 145*23
Test Required : Oxidation induction time (OIT)
Test Method : With reference to ASTM D3895-07, analysis was performed by DSC.
Date of Receipt : Feb.23,2011
Test Period : Feb.23,2011 to Mar.3,2011

Test result(s) : For further details, please refer to the following page(s)

***** To be continued*****

Signed for SGS-CSTC Standards
Technical Services (Shanghai) Co., Ltd

Ivy Zhu

Ivy Zhu
Authorized signatory

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, jurisdiction and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and, within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.



6th building, No.69, Block 1158, Kangjiao East Road, Pudong District, Shanghai, China 201319

中国·上海·上海浦东康桥东路1159弄69号8号楼 邮编: 201319

t (86-21) 61196300

t (86-21) 61196300

f (86-21) 68183920

f (86-21) 68183920

www.cn.sgs.com

e sgs.china@sgs.com

Member of the SGS Group (SGS SA)

TEST REPORT

No. : SHMR110201114

Date : Mar.3,2011

Page: 2 of 3

Sample description: Sheet

Test Condition:

Test temperature: 200°C


Oxygen: 50ml/min

Type of pan: Aluminum

Test Result:

OIT: 42.6min

DSC curve:



***** To be continued*****

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, jurisdiction and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its issuance and is not intended to be used for any other purpose. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

